

# Verarbeitungsblatt

Futado Harz / Status: 10.2026

## Beschreibung

Das Futado Harz ist die Flüssigkomponente zur Herstellung der Futado Wand- und Bodenbeschichtung.

Das Futado Boden- und Wand System besteht aus drei Komponenten:

- Komponente A – Futado Harz
- Komponente B – Futado Pigmentierung
- Komponente C – Futado Boden- und Wand weiß

## Verarbeitung

Die Materialien sollten für fachgerechte Verarbeitung 24-48 h vor Verarbeitung ab einer Raumtemperatur von min. 15°C trocken gelagert werden.

Nicht unter +8 °C Luft- und Objekttemperatur verarbeiten. Ideal bei +15 °C bis +20 °C Luft- und Objekttemperatur zu verarbeiten.

Futado Harz bindet innerhalb von 60 Minuten vollständig ab. Die Topfzeit beträgt ca. 30 – 40 Minuten.

Die 2.Lackschicht sollte nach 12-24 Stunden aufgebracht werden, nicht früher.

Komponente A,B,C reichen bei doppeltem Auftrag für 8-9 m<sup>2</sup>

## Sicherheitshinweise

Berührungen mit den Augen und der Haut vermeiden. Wir empfehlen, mit Arbeitshandschuhen sowie Schutzbrille zu arbeiten. Vor Kindern sicher aufbewahren.

## Entsorgung

Gewerbliche Entsorgung:

EAK-N°: 170904 (Bau- und Abbruchabfälle).

Abfallschlüssel-N°: 080112 (Farb- und Lackabfälle ohne Lösemittel)

## Anmerkung

Der Inhalt begründet kein vertragliches Rechtsverhältnis und ist nur unverbindlich beratend. Der Verarbeiter/Käufer wird nicht davon entbunden, unsere Produkte auf ihre Eignung für die vorgesehene Anwendung in eigener Verantwortung zu prüfen.

Darüber hinaus gelten unsere Allgemeinen Geschäftsbedingungen. Mit Erscheinen einer Neuauflage dieses Praxismerkblattes mit neuem Stand verlieren die bisherigen Angaben ihre Gültigkeit.

Die jeweils aktuelle Version ist auf [volimea.de](http://volimea.de) aufzufinden.



High quality and tested products




Natural ingredients



Suitable for allergy sufferers



High durability and resilience



Jointless floor and wall coating



Levelling out uneven surfaces

San Marco Coatings Deutschland GmbH products are manufactured exclusively for professional applicators who have a basic knowledge of the handling and use of chemical and technical products for surface design. The processing instructions for our qualities given in the data sheets are to be regarded exclusively as non-binding recommendations and do not constitute any guarantee. These recommendations are based on our experience and test series and are intended to facilitate the work of our customers. Any possible deviation from the ideal working conditions is the responsibility of our customers and may affect the result of the application. However, this does not release the customer from his obligation to check the product and its suitability for the surface to be treated, preferably by trial application. In case of any doubts regarding the handling or processing of the purchased product, our sales staff and technicians will provide you with information to the best of their knowledge. It goes without saying that San Marco Coatings Deutschland GmbH guarantees the perfect quality of its products in accordance with the respective product specifications, but the responsibility for the use of the products supplied lies exclusively with the purchaser. Unless we have expressly warranted specific properties and suitability of the products for a contractually determined purpose, any advice or information on application technology, although given to the best of our knowledge, is in any case non-binding and does not constitute a warranty of any kind. San Marco Coatings Deutschland GmbH shall be liable for the use of its products by its customers in accordance with its General Terms and Conditions of Sale and Delivery, to which the customer's attention is hereby drawn. The current Technical Data Sheet can be downloaded from our website. After publication of a new edition, the validity of previous technical data sheets expires. Status: 2026-01-10.